

Product Data Sheet ELKEM MICROSILICA[®] 940 Concrete applications

Elkem ASA Silicon Products Drammensveien 169 P.O. Box 334 Skøyen NO-0213 OSLO Fax: +47 22 45 01 11 www.elkem.com

Description ELKEM MICROSILICA[®] 940 is a dry silica fume powder. In use, ELKEM MICROSILICA[®] 940 improves the properties and performance of high performance concrete and specialist mortar formulations.

It acts physically to optimise particle packing of the mixture, and chemically as a highly reactive pozzolan.

ELKEM MICROSILICA[®] 940 is available in two forms: Undensified (U) and Densified (D).

Chemical &	Property	Unit	Value
physical data	SiO ₂	%	Minimum 90.0
	H ₂ O (when packed)	%	Maximum 1.0
	Loss of ignition	%	Maximum 3.0
	Retained on 45µm	%	Maximum 1.5*
	Bulk density U	kg/m³	200 - 350
	Bulk density D	kg/m ³	500 - 700
	Test methods are available on request. For typical analysis of minor elements, please contact our Elkem representative. *Tested on undensified		
Packaging	The product is available in 25 kg bags, various other size bags and bulk road tanker. Please contact our representative for more details.		
Storage and handling	ELKEM MICROSILICA [®] 940 should be stored in dry conditions and not exposed to moisture.		
Health, safety & environment	Refer to Product Safety Information (PSI) document on our website: <u>www.elkem.com</u>		
Quality assurance	Elkem Silicon Products management system for development, processing and supply of ELKEM MICROSILICA [®] is certified to ISO 9001:2015. The chemical and physical properties of ELKEM MICROSILICA [®] 940 are regularly tested.		
Sustainability	For Elkem, sustainability is central to our business strategy. Our mission is to provide advanced material solutions shaping a better and more sustainable future, adding value to our stakeholders globally. We are committed to reducing embodied carbon emissions. For further information, please visit <u>www.elkem.com/sustainability/</u> or contact us to learn more about our sustainability roadmap.		
Additional Information and contact	See additional Elkem data sheets and technical papers on our website: <u>www.elkem.com</u> . All data listed are reference values subject to production related tolerances. Although reasonable care has been taken in the preparation of the information contained herein, it still remains the duty of the user to prove the suitability of this material for their application.		

ELKEM MICROSILICA® is a registered trademark of Elkem ASA.

This product data sheet is property of Elkem ASA and may not without its written permission be used, copied or made available to others. The receiver is responsible for any misuse. © Copyright Elkem ASA