

Product data sheet SIDISTAR® MB F21

Elkem ASA Silicon Products Drammensveien 169 P.O. Box 334 Skøyen NO-0213 OSLO www.elkem.com

Description

SIDISTAR® Master-Batch series are designed to provide you with easy dispersibility of Sidistar® in thermoplastics. Sidistar® MB F21 contains 50% of Sidistar® T120U in an ethylene acrylate carrier.

Applications

SIDISTAR® MB F21 has been designed for usage in thermoplastics. Areas of use include flame retardant compounds; foamed PVC; deck board / sheets; wood-plastic composites etc. The product has excellent compatibility with; PVC; ABS; PA; PET and Polyolefins.

Chemical analysis & physical data

Properties	Test Method	Unit	Limits
Density	EN ISO 1183	g/cm³	1,29 ± 0.3
Properties	Test Method	Unit	Typical Values**
Melt temperature (DSC) Bulk density (when packed)	ISO 11357 ESM-LAB-08	°C kg/dm³	95 0.746 ± 0.1
Vicat softening point (10N, 50 °C/h)	ISO 306	°C	73.5
Tensile Strength	EN 60811	N/mm²	9.4
Elongation at break	EN 60811	%	70.7
H ₂ O content (when packed)	ESM-LAB-02	%	0.05

^{**} Typical values are for indicational use only, values are not part of Elkem Silicon Materials standard analysis.



Product data sheet SIDISTAR® MB F21

Elkem ASA Silicon Products Drammensveien 169 P.O. Box 334 Skøyen NO-0213 OSLO www.elkem.com

Packaging

Bags on pallet	1 big bag	60 small bags
Bag material	Coated woven polypropylene fabric	LDPE bag
Cover / protection	LDPE shrink hood	LDPE shrink hood
Pallet	Fumigated wood	Fumigated wood
Dimensions (metric)		
Not weight 1 had	1000 kg	20 kg

1000 kg	20 kg
1000 kg	1200 kg
	1230 kg
	60 x 40 x 15 cm
	100 x 120 x 155 cm
	9

Dimensions (imperial)

Net weight 1 bag	44 lb
Net weight on pallet	2646 lb
Gross weight	2712 lb
Bag dimensions (L x W x H)	23.6 x 15.7 x 5.9 in
Discharge spout Pallet dimensions incl bags (L x W x H)	39.4 x 47.2 x 61 in

Storage and handling

The product is recommended to be stored in a covered dry place, protected from direct UV light. Recommended storage temperature between +5 °C and +40 °C (+45 °F and +104 °F). It's important that the minimum temperature is > 5 °C (9 °F) above the dew point. Recommended relative humidity < 85 %.

Shelf life

We recommend that the product should be used within 2 years from production date

Health, safety & environment

The product safety information, as well as REACH information, can be found on our website: www.sidistar.com.

Quality assurance

Elkem's management system is certified to ISO 9001:2015.

Sustainability

For Elkem, sustainability is central to our business strategy. Our mission is to provide advanced material solutions shaping a better and more sustainable future, adding value to our stakeholders globally. We are committed to reducing in embodied carbon emission. For further information, please visit www.elkem.com/sustainability/ or contact us to learn more about our sustainability roadmap.

Additional Information and contact

For further information about SIDISTAR®, a contact list can be found on our webpage www.sidistar.com

Sidistar® is a registered trademark of Elkem ASA.

This product data sheet is property of Elkem ASA and may not without its written permission be used, copied or made available to others. The receiver is responsible for any misuse. © Copyright Elkem ASA