

Product data sheet Elkem Microsilica® 971

Elkem ASA Silicon Products

Drammensveien 169 P.O. Box 334 Skøven NO-0213 OSLO Tel: +47 22 45 01 00 www.elkem.com

Description Elkem Microsilica® is a key ingredient in advanced low and ultra-low cement castables.

It is highly reactive during sintering, which leads to improved ceramic bonding at

reduced firing temperatures.

Applications Elkem Microsilica® is used in castables, gunning mixes and other shaped and unshaped

materials.

Features Elkem Microsilica® 971 is offered both as Undensified (971-U) and Densified (971-D).

Benefits Improved flow - easier to cast

Improved particle packing - denser castables

Gel-bonding

Improved hot-strength properties

Chemical analysis & physical data

Weight% SiO ₂ (diff.)	Spec*	Typical** 97
C _{free} ***	max. 0.8	0.59
Fe ₂ O ₃	max. 0.1	0.07
Al_2O_3	max. 0.3	0.20
CaO	max. 0.4	0.29
MgO	max. 0.2	0.18
K ₂ O	max. 0.3	0.22
Na ₂ O	max. 0.3	0.25
P_2O_5	max. 0.10	0.04
SO ₃	max. 0.3	0.17
CI	max. 0.10	0.01
H ₂ O ****	max. 0.5	0.20

Properties	Spec*	Typical**
Loss on Ignition	% max. 0.8	0.54
Coarse Particles >45µm	% max. 0.5	0.25
pH-value	5.5-7.8	7.2
Bulk density ****		
Undensified 971-U	kg/m ³ 250-350	300
Densified 971-D	kg/m ³ 450-550	500

^{*} Test methods are available upon request

Packaging

The product is available in 25 kg small bags and various sized big bags. Please contact our sales representative for more details.

Storage and handling

Avoid dust generation

Store material properly, protected from moisture and contamination

Health. safety & environment Please consult our Product Safety information on our website: https://www.elkem.com/silicon-products/refractories/microsilica/page-1/.

Sustainability

For Elkem, sustainability is central to our business strategy. Our mission is to provide advanced material solutions shaping a better and more sustainable future, adding value to our stakeholders globally. We are committed to reduction in embodied carbon emission. For further information, please visit www.elkem.com/sustainability/ or contact us to learn more about our sustainability roadmap.

Additional information and contact

For further information, please contact our local sales representative. Our specialists will assist you in solving individual problems.

Elkem Microsilica® is a registered trademark of Elkem ASA.

This product data sheet is property of Elkem ASA and may not without its written permission be used, copied or made available to others. The receiver is responsible for any misuse. © Copyright Elkem ASA

^{**} Typical values are for guidance only
*** C in SiC is not included

^{****} When packed