

Product Data Sheet Silgrain® HQ MicronCut

Elkem ASA Silicon Products Drammensveien 169 P.O. Box 334 Skøyen NO-0213 OSLO www.elkem.com

Description Silgrain® HQ MicronCut is a high purity micronised silicon powder.

Applications Raw material in the ceramic industry.

Chemical analysis & physical data

	Typical	Min	Max
Si wt%*	99.8	99.7	-
Fe wt%	0.04	0.02	0.05
AI wt%	0.09	0.07	0.12
Ca wt%	0.013	0.005	0.02
Ti wt%	0.001	0.001	0.005
B ppmw	30	-	35
P ppmw	25	-	35

Other trace elements on request. Fe, Al, Ca and Ti measured by XRF (X-ray fluorescence). P and B measured by ICP (Inductively Coupled Plasma). Si wt%* = 100 wt% -Fe wt% -Al wt% -Ca wt% -Ti wt% -0.1 wt%. The 0.1 wt% is subtracted as a lump sum of other metallic elements in silicon.

Typical sizes are 0-10 μm, 0-45 μm and 0-75 μm. Other sizes can be delivered upon Sizing

request. All Silgrain® HQ MicronCut products have a well-defined top cut with max. 1

vol% oversize according to laser diffraction analysation.

Silgrain® HQ MicronCut is typically delivered in 25 kg paper bags or 1000 kg big bags. **Packaging**

Storage and handling

Store under dry conditions. Avoid handling that generate dust build-up. Avoid ignition

sources (e.g. welding) in areas with high dust concentrations.

Shelf life Unlimited when stored under dry conditions.

Health, safety & environment

The product does not meet the criteria for hazard classification according to Regulation (EC) No 1272/2008 (CLP) and UN GHS (7th rev.). For more information, please refer to Elkem Product Safety Information No. 302.

Quality assurance Elkem's management system is certified to ISO 9001:2015.

Sustainability

Elkem's climate roadmap is detailing how the company plans to develop its business in line with the aim of the Paris Agreement of limiting global warming to well below two degrees. The company aims to reduce its total fossil CO₂ emissions by 28% from 2020 to 2031. Elkem's long-term goal is net zero emissions by 2050. For further information, please visit www.elkem.com/sustainability/.

Climate change (IPCC2013 GWP 100a v1.03): 5,94 kg CO₂ eq / kg. Calculation from 2020 based on 2018 and 2019 actual production data including scope 1, 2 and 3.**

Additional Information and contact

For further information please contact our Elkem sales representative via our contact form: https://content.elkem.com/contact-silicon-products.

Silgrain® is a registered trademark of Elkem ASA.

This product data sheet is property of Elkem ASA and may not without its written permission be used, copied or made available to others. The receiver is responsible for any misuse. ©Copyright Elkem ASA.

^{**}Elkem drafts content with due care and is constantly improving the LCA quality and methodology. Please contact us directly for more information.